## Material Safety Data Sheet

# U.S. Department of Labor

May be used to comply with

OSHA's Hazard Communication Standard, 29 CFR 1910.1200. Standard must be consulted for specific requirements.

Occupational Safety and Health Administration (Non-Mandatory Form) Form Approved OMB No. 1218-0072

Freshly Mixed Unhardened Concrete	Note: Blank spaces are not permitted. If any item is not applicable, or no information is available, the space must be marked to indicate that.
	space must be marked to mulcate that.

#### Section I

Manufacturer's Name EZform Inc.	Emergency Telephone Number 770-913-8363
Address (Number, Street, City, State, and ZIP Code) 120 Camp St. Suite B	Telephone Number for Information 770-913-8363
Loganville, GA 30052	Date Prepared
	Signature of Preparer (optional)

Section II - Hazard Ingredients/Identity Information

Hazardous Components (Specific Chemical Identity; Common Name(s))	OSHA PEL	ACGIH TLV	Other Limits Recommended	%(optiona
Formula - Mixtures of Portland or blended cements, concrete aggregates and chemical admixtures.				
Portland and blended cements:				
Tricalcium Silicate (3CaO-SiO $_2$ ) (CAS # 12168-85-3)				
Dicalcium Silicate (2CaO-SiO <sub>2</sub> ) (CAS # 10034-77-2)				
Tricalcium Aluminate (3CaO-Al <sub>2</sub> O <sub>3</sub> )	calcium Aluminate ( $3CaO-Al_2O_3$ ) (CAS # 23042-78-3)			
Tetracalcium Aluminoferrite (4CaO-Al <sub>2</sub> O <sub>3</sub> -Fe <sub>2</sub> O <sub>3</sub> )	etracalcium Aluminoferrite ( $4CaO-Al_2O_3-Fe_2O_3$ ) (CAS # 12068-35-8)			
Calcium Sulfate Dihydrate (CaSO <sub>4</sub> -2H <sub>2</sub> O) (Gypsum) (CAS # 7778-18-9) PEL-TWA 15 Mg/M³ Total Dust				otal Dust
Plus traces of Calcium Oxide (CaO), Magnesium Oxide (MgO), Potassium Sulfate ( $K_2SO_4$ ), and Sodium Sulfate ( $Na_2SO_4$ )				
Other Ingredients:				
Concrete Aggregates, Inert gravel, sand and rocks				
Admixtures may include fly ash, granulated slag and very small amounts of organic and inorganic materials which have no effect on the hazards associated with the use of the product.				

### **Section III - Physical/Chemical Characteristics**

Boiling Point	N/A	Specific Gravity (H <sub>2</sub> O = 1)	2.28 - 2.42
Vapor Pressure (mm Hg.)	N/A	Melting Point N/A	
Vapor Density (AIR = 1)	N/A	Evaporation Rate (Butyl Acetate = 1)	N/A
Solubility in Water	Slight (0.01 to 1%)	PH for Plastic Concrete	12.5
Appearance and Odor	Gray, plastic, flowable, granular composite - Faint odor		

**Section IV - Fire and Explosion Hazard Data** 

Flash Point (Method Used) N/A	Flammable Limits	N/A LEL A	N/ UA	EL N/
Extinguishing Media N/A				
Special Fire Fighting Procedures N/A				
Unusual Fire and Explosion Hazards N/A				


(Reproduced in June 1999 By Ohio Ready Mixed Concrete Association)

Based on OSHA 174, Sept. 1985

#### Section V - Reactivity Data

Stability	Unstable		Conditions to Avoid		
	Stable	X	However the product stiffens and hardens in 2 to 8 hours and is no longer hazardous		
Incompatibility (I	Incompatibility (Materials to Avoid) None				
Hazardous Decomposition or Byproducts Product hardens in a few hours and then does not decompose					
Hazardous Polymerization	May Occur		Conditions to Avoid None		
	Will Not Occur	X			

#### Section VI - Health Hazard Data



Material Safety Data Sheet - OSHA 174 8/30/05 10:19 PM

Protective Gloves Yes - waterproof

Eye Protection Yes - tight fitting goggles

Other Protective Clothing or Equipment Waterproof boots, long-sleeved shirt and full length trousers should be worn

Work/Hygienic Practices Avoid contact between skin/eyes and wet/moist concrete

Page 2

\* U.S.G.P.O.: 1986 - 491 - 529/45775